

Scattered Light Photoelastic Stress Meter

Model: SLP-1000

Price JPY4,000,000-

This machine is available to measure stress distribution of chemically tempered glass which is strengthened by ion-exchange from Li⁺ to Na⁺ using scattered light photoelasticity. In case of that the glass is strengthened by mixed liquid KNO₃ and NaNO₃, K⁺ layer should be measured by FSM-6000LE and Na⁺ layer should be measured by SLP-1000. These data can be combined by special software.



- ❖ Don't depend on refractive index distribution
- ❖ Available for bent glass
- ❖ High resolution
(Laser diameter: about 10um)
- ❖ Measurement data from SLP can be combined with one of FSM

* The combination requires optional FsmV dongle.

Specification

Measurement range	: CS 0-2000MPa, DOL 10-400um
Measurement resolution	: Stress ±5MPa Depth ±5um
Measurement precision	: 50um or deeper from surface Stress ±10Mpa Depth ±10um
Light source	: LD (Wavelength 640nm) 30mw Class 3B
Application	: Chemically tempered glass, DIOX glass Thermally tempered glass
Sample shape	: Flat-1000R 10x10mm or more
Prism	: nD=1.516
PC	: Preinstalled OS, special software
OS	: Windows 10 professional edition
Size (main body)	: W320xD280xH220mm
Weight (main body)	: 10kg

Orihara Industrial Co., Ltd.

5-47-15 Higashi-Ikebukuro Toshima-ku Tokyo Japan 170-0013

TEL 03-3985-9531 FAX 03-3985-9532

<http://www.orihara-ss.co.jp> e-mail orihara@orihara-ss.co.jp